

## **SPECIFICATIONS**

Concrete Min. Strength: 4,000 psi at 28 days Reinforcement: #4 bar gr. 60, Forta Fiber 5 lb/cy

Air Entrainment: 6%

Construction Joint: Butyl Rubber Sealant Pipe Connection: Polylok Seal (patented)

Weight = 6,900 lbs Load Rating: 300 psf

## LOW PROFILE SEPTIC TANKS MODEL LB-750 / 750 GALLONS

**Woodard's Concrete Products, Inc.** 

629 Lybolt Road, Bullville, NY 10915 (845) 361-3471 / Fax 361-1050

Page 9A 10/28/15